



Preliminary technical data sheet-
LOCTITE® EA E-30HV
Product 3981

Medical Products, June 2002 Feb 27, 2014

PRODUCT DESCRIPTION:

LOCTITE® EA E-30 HV is a high-viscosity, industrial grade epoxy adhesive. Once mixed, the two-part epoxy system develops fast fixture strength and cures within 24 hrs with minimal shrinkage. When fully cured, the epoxy withstands exposure to a wide range of chemicals and solvents, and has excellent dimensional stability over a wide temperature range. LOCTITE® EA E-30 HV has good balance of flow characteristics and thixotropic behavior at low shear that ensures applications in vertical and horizontal surfaces with 1-2 mm gap filling and partially non sagging properties.

TYPICAL APPLICATIONS

LOCTITE® EA E-30 HV is designed for bonding, potting, staking and laminating applications where excellent structural, mechanical, and electrical insulating properties are required. It bonds well to most materials including glass, optical fibers, ceramics, metals, and many rigid plastics. The high thermal conductivity provides good heat dissipation for thermally sensitive components.

Typical applications include bonding transformers, transistors and other heat generating electronic components to printed circuit board assemblies or heat sinks

LOCTITE® EA E-30 HV Characteristics:

Chemistry	Filled epoxy and amine hardener
Type	Bisphenol A based resin
Appearance	Off white
Pot life	30 min
% Solids	100%
Recommended cure for handling Strength @ 25°	4 hour
Minimum cure time @ 25°C	16-24 hrs

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A	Value	Range
Viscosity, Brookfield- 25 °C, mPa·s (cP):	35000	29000-40000
Weight per Gallon, lbs/gal	14.6	14.5-14.8

Part B	Value	Range
Viscosity, Brookfield- 25 °C, mPa·s (cP):	23000	19000-26000
Weight per Gallon, lbs/gal	11.8	11.5-12.5

Mixed:	Value	Range
Viscosity, Brookfield- 25 °C, mPa·s (cP):	40000	34000-41000
Mixed ratio (A:B) By weight	100:29	
By Volume	100: 36	

TYPICAL CURING PERFORMANCE

Curing Properties	Typical Value
Working life 70 gm @ 25 ° C	30 min
Fixture Time 1gm @ 25 ° C	240min

TYPICAL PROPERTIES OF CURED MATERIAL
 (@ 25 °C unless noted)

	Typical Value
Dielectric Strength, KV/mm	19.2
Volume Resistivity, fi-cm	1.84 x 10 ¹⁴
Mod. Of elasticity, ASTM D 638-2010, N/mm ²	7960
CTE, µmm / mm °C	38
Hardness ASTM D-1706, Shore D	85
Glass Transition Temperature, Tg, °C	55
Thermal Conductivity, Wm/K	0.6

PERFORMANCE OF CURED MATERIAL

Shear strength vs Substrate

(Leap Shear Cured at 25 °C for 24 hour)

	Typical Value N/mm ²
ABS	3.4 (sub. Fail)
SS	17.4
GBMS	15.9
AL	12.6

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use

Mixing:

1. Material temperature should be between 18 °C to 27 °C.
2. Add part A to the container and add part B to it while mixing at appropriate mixing ratio.
3. Mixing time should be 2-5 min.

Application Method:

1. Apply fully mixed material to the surface.
2. Ensure that all mixed materials dispensed before 30 min, preferably before 20 min (typically for 70gm @ 25 °C). Large quantities and/or higher temperature will reduce this working time.
3. For maximum bond strength apply adhesive evenly to both surfaces to be joined.

NOT FOR PRODUCT SPECIFICATIONS
 THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY
 PLEASE CONTACT HENKEL ADHESIVES TECHNOLOGIES TECHNICAL DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT

JEJURI, PUNE, INDIA 412 303 Ph +91 2115300000 FAX + 91 2115 253248



4. Cure the material for minimum of 24 hour at 25 °C for high strength.
5. Excess uncured adhesive can be clean up with ketone type solvents.
6. Alternatively, LOCTITE® EA E-30 HV can be applied using supply pump auto dispensing unit using static mix nozzle. Henkel TCS group can provide specific details of the meter mix equipment.

Caution:

Technical Tips for Working with Loctite® Working time and cure depends on temperature and mass:

- The higher the temperature, the faster the cure.
- The larger the mass of material, the faster the cure.

LMS

Loctite Material Specification

LMS dated Oct 15, 2013. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Loctite Quality.

Storage

Store product in the unopened container in a dry location. Material removed from containers may be contaminated during use. Do not return liquid to original container. Storage information may be indicated on the product container labeling. **Optimal Storage: 18 °C to 25 °C. Storage below 10 °C or greater than 30 °C can adversely affect product properties.** Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those recommended. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The developmental product for which the data provided herein is furnished for informational purposes only and are believed to be accurate and reliable. Nevertheless, Henkel Corporation cannot and will not assume responsibility for the results obtained by others over whose production methods we have no control. Thus, it is the user's responsibility to determine the suitability of this developmental product for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling, storage, disposal and use thereof. In light of the foregoing, **HENKEL CORPORATION SPECIFICALLY DISCLAIMS ANY AND ALL WARRANTIES EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE AND FREE FROM CLAIMS OF THIRD-PARTY PATENT INFRINGEMENT, ARISING FROM THE SALE, POSSESSION, HANDLING, STORAGE, DISPOSAL, TRANSPORTATION OR USE OF THIS DEVELOPMENTAL PRODUCT. HENKEL CORPORATION SPECIFICALLY DISCLAIMS ANY LIABILITY FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES OF ANY KIND, INCLUDING LOST PROFITS.** Neither the developmental product, nor the data or discussion herein of various processes for which, are to be interpreted as an express or implied license under any Henkel Corporation patents. Henkel Corporation recommends that any and all proposed commercial application(s) using this developmental product be evaluated for reproducibility in the exact manner and on the production equipment with which it is intended to be used before repetitive commercial production use, using this data as a guide. This developmental product may be covered by one or more United States or foreign patents or patent applications of Henkel Corporation, or under which Henkel Corporation is licensed.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.1

NOT FOR PRODUCT SPECIFICATIONS
 THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY
 PLEASE CONTACT HENKEL ADHESIVES TECHNOLOGIES TECHNICAL DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT
 JEJURI, PUNE, INDIA 412 303 Ph +91 2115 300000, FAX + 91 2115 253248

Note: The information contained herein are typical values intended for reference and comparison purposes only. They should NOT be used as a basis for design specifications or quality control. All values at 23°C unless otherwise noted.